

Product information | TECHNICAL DATA SHEET

SYNTHETIC VARNISH. To protect and ennoblecer.
400 ml, 10.54 Oz, 312 g.

GENERAL DESCRIPTION

Alkyd varnish protector (synthetic resin) over fast drying. Available in matte, glossy and satin finish. Due to its characteristics we recommend using on wood although it may also be used to varnish various surfaces.

FEATURES

- Very fast drying.
- Excellent elasticity.
- Easy to apply and recoat.
- Good hardness.
- Good resistance outdoors.
- High durability shine.
- Resistance U.V.
- Highly resistant to scratches once the film has been polymerized.
- **Attention:** Over time, light colored surfaces tend to become yellowed.

APPLICATIONS

Due to the product characteristics, its use is recommended for retouching and painting materials of all kinds:

- DIY
- Plumbing
- Aluminium carpentry
- Industry
- Automotive
- Wood

On newly painted surfaces or old paint, do a test first in order to see the results, as the varnish may crack the previous layer.

INSTRUCTIONS FOR USE

- Before using, shake the aerosol vigorously for approximately one minute after the noise of the mixer starts.
- Apply over clean and dry surfaces. When varnishing iron remove corrosion with a wire brush. In plastics like PS and PP apply first a primer layer. See product's behavior in any plastic surface.
- Apply thin coats for better results, better three thin layers than a thick one. Recoatable after 30 minutes using the same lacquer.
- Do not apply on plugged-in electrical equipment and use in well-ventilated areas.
- Ask for MSDS

PHYSIC CHARACTERISTICS

Binder:	Acrylic
Color:	Transparent slightly yellowish
Shine 60° (ASTM D-523 ISO 2813):	>80 shining; 40-60
	Satin; <10 Mate
Dry touch (ASTM D-1640 ISO 1517):	30'
Cured (ASTM D-1640 ISO 1517):	24h
Dry film thickness (ASTM D-823 ISO 2808):	15 µ/ layer
Adhesion (ASTM D-3359 ISO 2409):	3 B
Theoretical yeled (pintado en continuo):	2,5 m²
Solvent:	Mix
Product life:	> 5 years
Recoating:	10'-2h or after 24-48h
Heat resistance:	100°C
Application conditions:	T° min 8°C
	T° surface 5°C a 50°C
	Humidity max 85 % R.H.P

* The adhesion tests were conducted on PP (modified EPDM). Date last review: 31/01/2017

IMAGE



LABEL



CAP SYSTEM



Sintético Satinado / Satin Synthetic EX014PR0904	Sintético Mate / Matt Synthetic EX014PR0907	Sintético Brillo / Gloss Synthetic EX014PR0900
---	--	---

PACKAGING

Nominal capacity: 400 ml.
Heat resistance of packaging: <50°C
Propellant: DME

Box (6 units)
205 X 140 X 200 mm.

