

Product information | TECHNICAL DATA SHEET

MEGA PLATA. Metallic silver colour. Glossy paint, high pressure, high covering and high powered. 600 ml, 16.75 Oz, 475 g.

- DIY

GENERAL DESCRIPTION

Mega Plata in a 600 ml format allows you to paint larger surfaces in less time. Gloss enamel, formulated with very high quality resins and leafing aluminium. With a very fast drying action, it leverages the power of the valve to expel the paint at high speed, obtaining a much wider span and a more fluid coat of paint. For a perfect finish and optimum exterior resistance.

FEATURES

- Very fast drying.
- High covering capability.
- Good adhesion.
- Does not contain lead
- Light weather resistance.
- Leafing type aluminum.
- It doesn't resist abrasion.

APLICACIONES

Very suitable for painting any type of surface, giving a highly decorative metallic aspect. Very suitable for artworks.

GraffitiPlasticsDecorationFine artsRetouching metallic components

Paint with low exterior resistance and low resistance to abrasion, which leads to a loss of the metallic appearance. Do not apply coats of varnish or other paints due to the leafing aluminium, which migrates to the surface.

INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute.
 Does not contain mixture balls inside.
- Apply to clean, dry surfaces. On rusty metallic surfaces remove rust with a wire brush and prepare an anti-rust primer if considered necessary.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within fifteen minutes with the same paint.
- Turn the aerosol upside down to clean out the valve after use, If the nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

PHYSICAL PROPERTIES

Binding type:	Special resin
Color:	Gloss silver
Dry to the touch (ASTM D-1640 ISO 1517):	10'
Completely dry (ASTM D-1640 ISO 1517):	30'
Thickness of dry layer (ASTM D-823 ISO 2808):	25 micras/layer (2 coats)
Adherence (ASTM D-3359 ISO 2409):	3 B
Theorical yield (continuous painting):	9,6 m ² for 600 ml
Thinner:	Aromatic mixture
Product life:	(Well Stored) 10 Years
Condition for application:	Minimum room temperature 8°C
	Surface temperature 5°C a 50°C
	Max humidity 85% R.H.P
Heat resistance of paint:	150°C
Recoating:	After 15'

^{*} All of the adherence tests have been carried out on iron plates. 250121

IMAGE



LIDProtects the valve

and the nozzle.

LABEL CAP SYSTEM













PACKAGING

High pressure. Heat resistance of packaging: <50°C Propellant: GLP - HC C3-C4 Nominal capacity: 600 ml.

Box (6 units) 200 X 280 X 140 mm.

